

IN THE CLAIMS

Please amend the claims as follows:

Claims 1-9 (Canceled).

Claim 10 (Previously Presented): A method of forming an article comprising,  
contacting fibrous and/or granular substrates with a thermally polymerizable mixture,  
and  
polymerizing the thermally polymerizable mixture to form the article,  
wherein the thermally polymerizable mixture comprises a multifunctional  
macromonomer and a radical polymerization initiator,  
wherein the multifunctional macromonomer comprises at least one free-radically  
polymerizable group selected from the group consisting of an acrylate group, a methacrylate  
group, a maleate group, a vinyl ether group, a vinyl group, and an allyl group, and  
wherein the thermally polymerizable mixture does not comprise monomers other than  
the multifunctional macromonomer.

Claim 11 (Previously Presented): The method of claim 10, wherein the substrates are  
selected from the group consisting of glass fibers, natural fibers, manufactured fibers, rock  
wool, core sand, and combinations thereof.

Claim 12 (Cancelled).

Claim 13 (Previously Presented): The method of claim 10, wherein the molar mass  
 $M_w$  of said multifunctional macromonomer is in the range from 300 to 30,000.

Claim 14 (Previously Presented): The method of claim 13, wherein the molar mass  $M_w$  of said multifunctional macromonomer is in the range from 500 to 20,000.

Claim 15 (Previously Presented): The method of claim 10, wherein said multifunctional macromonomer is obtained by a process comprising co-reacting

- a) 0.5-2.0 equivalents of a 2- to 6-hydric alkoxyated alcohol with
- b) 0 to 1 equivalent of a 2- to 4-basic  $C_3$  to  $C_{16}$  carboxylic acid and/or anhydride  
and
- c) 0.1 to 1.5 equivalents of acrylic acid and/or or methacrylic acid
- d) 0 to 1 equivalent of diol

to form a reaction product, and

reacting the reaction product with at least one epoxy compound.

Claim 16 (Previously Presented): The method of claim 15, wherein the process for forming the multifunctional macromonomer further comprises after reacting the reaction product with at least one epoxy compound, reacting the multifunctional-macromonomer with a polyisocyanate, optionally in the presence of a chain extender, to form a macromonomer comprising acrylate and polyurethane groups.

Claim 17 (Previously Presented): The method of claim 10, wherein said polymerization initiator is at least one selected from the group consisting of peroxides, hydroperoxides, peroxydisulfates, percarbonates, peroxyesters, hydrogen peroxide and azo compounds.

Claim 18 (Previously Presented): The method of claim 10, comprising 0.05% to 15% by weight solids of the polymerization initiator.

Claim 19 (Cancelled).

Claim 20 (New): The method of forming an article according to Claim 10, wherein the thermally polymerizable mixture is polymerized by heating to a temperature from 180 to 220°C.

Claim 21 (New): The method of forming an article according to Claim 10, wherein the fibrous and/or granular substrate is impregnated with 2% to 35% by weight, based on the weight of the substrate, of the thermally polymerizable mixture.

Claim 22 (New): The method of forming an article according to Claim 10, wherein the fibrous and/or granular substrate is impregnated with 5% to 25% by weight, based on the weight of the substrate, of the thermally polymerizable mixture.

Claim 23 (New): A method of forming an article according to Claim 10, wherein the thermally polymerizable mixture consists essentially of the multifunctional macromonomer and a radical polymerization initiator.

Claim 24 (New): A method of forming an article according to Claim 10, wherein the thermally polymerizable mixture consists of the multifunctional macromonomer and a radical polymerization initiator.

Claim 25 (New): A method of forming an article comprising;  
impregnating a fibrous and/or granular substrate with a thermally polymerizable mixture, and  
heating the impregnated substrate to temperature from 180 to 220°C to polymerize the thermally polymerizable mixture;  
wherein the thermally polymerizable mixture consists essentially of:  
(1) a multifunctional macromonomer having (a) at least one free-radically polymerizable group selected from the group consisting of an acrylate group, a methacrylate group, a maleate group, a vinyl ether group, a vinyl group, and an allyl group, and (b) a double bond content in the range from 0.1 to 1.0 mol/100g of macromonomer, and  
(2) a radical polymerization initiator..

Claim 26 (New): The method of forming an article according to Claim 25, wherein the thermally polymerizable mixture consists of:  
(1) the multifunctional macromonomer, and  
(2) the radical polymerization initiator.

Claim 27 (New): A method of forming an article according to Claim 10, wherein the multifunctional macromonomer has a double bond content in the range from 0.1 to 1.0 mol/100g of macromonomer.